



**24 ENGR CONSTR BDE
TESTING LABORATORY
BANGLADESH ARMY**

**24 ENGR CONSTR BDE TESTING LABORATORY
ZIA COLONY, DHAKA CANTONMENT, DHAKA-1206**

Revision no.: 01.	Effective from: Jun 2021	Doc. no.: 24 ECBTL/QF103
Issue no.: 02	Review date: May 2024	Page no.: 01 of 01

24 ECBTL no	: 24/JAP/Binder Course /PDL/2285/Test	Specimen condition	: Unsealed
Customer's ref no	: 3917/62/JS/Unnoyon	Specimen Source	:
Customer's name & add	: Property Development Ltd. (PDL)	Product code	: NA
Name of project	: Jolshiri Abasion Project	Sample dimension	: NA
Name of sub contractor	: NA	Relative humidity	: NA
Sample description	: 12&20 mm Stone Chips (Binder Course Material)	Temperature	: NA
Location/source	: Dubai	Date of sample receive	: 04-02-2024
Tested by	: Md. Nurul Amin Mirza	Date of test	: 05-02-2024

TEST REPORT

AGGREGATE CRUSHING VALUE (ACV) (Method-BS: 812-110)


Test no.		1	--
Total weight of sample (A)	gm	2891.4	--
Weight of sample passing 2.36 mm (no.8) sieve (B)	gm	566.5	--
Aggregate crushing value (ACV) (B/A)x 100	%	19.6	--
Average	%	19.6	

Test result	Specified limit	Remarks
20.0 %	****	****


05/02/24

Tested by

Lab Technician
HQ 24 Engr Constr Bde


05-02-24

Checked by

Asstt Tech Manager
HQ 24 Engr Constr Bde



Quality manager

Quality Manager
HQ 24 Engr Constr Bde

* The testing result/report is issued by 24 ENGR CONSTR BDE. This result/report refers only the particular item submitted to test.

END